

Description

One component moisture curing silicone based sealant and adhesive releasing non corrosive and low-odour by products. Provides an extremely flexible gasket between surfaces made of various materials (metal, plastics, glass, ceramics). Suitable for sealing gear boxes, pumps and motors flanges, oil and water containers, air forced pipes. Resistant to vibrations, thermal shocks, pressurized air, water, oils and several chemicals. Keeps its sealing properties within temperatures of - 50°C and + 180°C. Sealed parts can be disassembled using normal tools.

Physical properties

Composition : silicon neutral curing
Colour : black, grey
Appearance : paste
Specific weight (g/ml) : 1,40 - 1,50
Shelf life @ +25° C : 12 months in original unopened packaging

Curing properties

Tack free time : 15 - 30 minutes
Functional curing time : 3 - 6 hours
Final curing time : 24 - 36 hours

Physical properties after curing 7days/+23°C/UR 50% (typical)

Hardness Shore A (ASTM D-2240) : 25 ± 5
Tensile strength (ASTM D-412) : 0,5 - 1,0 MPa
Elongation at break (ASTM D-412) : 400 - 600 %
Temperature range : -65°C/ +180°C
Joint Movement Capability (ASTM C-290) : ± 25%
Dielectric strength (DIN 53481) : 18 kV/mm
Surface resistivity : 3 x 10¹⁵ Ω
Dielectric constant (1MHz) (DIN 53482) : 2,7

Directions for use

Clean and degrease parts to bond with Loxeal Cleaner 10. Apply enough product to fill the gap. The product is moisture curing therefore pieces shall be assembled rapidly. Allow full cure before putting stress on pieces assembled.

Storage

Keep product in a cool and dry room at no more than +25°C. To avoid contaminations do not refill containers with used product. For further information on applications, storage and handling contact Loxeal Technical Service.

Safety and handling

Consult Material Safety Data Sheet before use.

Note

The data contained herein, obtained in Loxeal laboratories, are given for information only; if specifics are required, please contact Loxeal Technical Department. Loxeal ensures abiding quality of supplied products according to its own specifics. Loxeal cannot assume responsibility for the results obtained by others which methods are not under Loxeal control. It is user's responsibility to determine suitability for user's purpose of any product mentioned herein. Loxeal disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Loxeal products. Loxeal specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.