

Description

Low viscosity instant adhesive based on alcoxy-ethyl cyanoacrylate.
Low odour non irritating, non-blooming effect, for appearance-sensitive assemblies.
Especially suitable to be used in non-ventilated or closed areas.

Physical properties

Composition: alcoxy-ethyl cyanoacrylate
Colour: clear/colourless
Viscosity (+25°C - mPa s): 10 - 20
Specific weight (g/ml): 1,06
Gap to fill: 10 - 40 microns
Flash point (ISO 2592): + 87°C
Shelf life: 12 months in original unopened packaging
Temperature range: -50°C/+80°C

Curing properties

Curing rate depends on the substrate used, on the gap, on the temperature and on the environmental humidity.

Substrate Fixture Time (seconds)

Plastics

* PVC: 10 - 30
* Phenolic Resin: 10 - 30
* ABS: 10 - 30

Metals

* Steel: 15 - 30
* Aluminium: 10 - 20
* Zinc: 20 - 60

Various substrates

*Neoprene/NBR: < 5


In case of too long setting time we recommend the use of Loxeal Activator 9. IN case of usage with PE, PP, Silicone rubbers or PTFE Loxeal Primer 7 is always recommended.

Proprieties of cured material (typical)

Tensile strength ISO 6922 (N/mm²): 10 - 20
Shear strength ISO 4587 (N/mm²): 14 - 22
Softening range: +150°C
Refraction index n²⁰_D: similar to glass
Electrical resistivity DIN 53482 (Ω mm): >10¹⁵
Dielectric strength ASTM D149 (kV/mm): 25
Dielectric constant DIN 53483 (1MHz): 3

Environmental resistance

The graph below shows the mechanical strength of the product (%) vs. temperature.
Specimen steel - ISO 4587



Chemical resistance

Aged at indicated temperature under conditions below after 24 hours from polymerisation.

Substance	°C	Resistance after 100 h	Resistance after 500 h	Resistance after 1000 h
-----------	----	------------------------	------------------------	-------------------------

Motor oil	40	discrete	discrete	discrete
Alcohol	25	excellent	excellent	excellent
Gasoline	25	excellent	good	discrete
Relative humidity 90%	40	low	null	null
Refrigerating gases	25	excellent	excellent	excellent

* For information on resistance with other chemicals, contact Loxeal Technical Service

Directions for use

Clean and degrease parts to bond with Loxeal Cleaner 10. Excess of product either cured or not can be removed with Loxeal CA Remover.

Storage

We recommend storing product in a cool and dry place at temperature non exceeding +20°C. For better and enhanced shelf life, keep product in a refrigerator at +2°C/+7°C. To avoid contaminations do not refill containers with used product. For more information on applications, storage and handling contact Loxeal Technical Service

Safety and handling

Consult the Safety Data Sheet before use.

Note

The data contained herein, obtained in Loxeal laboratories, are given for information only; if specifics are required, please contact Loxeal Technical Department. Loxeal ensures abiding quality of supplied products according to its own specifics. Loxeal cannot assume responsibility for the results obtained by others which methods are not under Loxeal control. It is user's responsibility to determine suitability for user's purpose of any product mentioned herein. Loxeal disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Loxeal products. Loxeal specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.